



SULPHUR, OIL 1% + SILICA 0.3%

PHYSICO-CHEMICAL CHARACTERISTICS

Composition : Ground elemental sulphur treated with oil and silica

QUALITATIVE CHARACTERISTICS

Assay	% S	> 98
Oil	%	1 ± 0.2
Loss on weight at 100°C	%	< 0.2
Ash	%	< 0.4
Acidity	% H ₂ SO ₄	< 0.1
Residue on 45 µm sieve	%	< 20%
Residue on 90 µm sieve	%	< 2%
Residue on 180 µm sieve	%	< 0.01%

The indicated values are intended as determined according to our standard analysis methods.

STANDARD PACKAGING

20 and 25 kg bags on pallets
 Various sizes bulk bags on pallets

MAIN USES

In the rubber industry as a vulcanizing agent.

FOR HANDLING INFORMATION PLEASE CONSULT THE SAFETY DATA SHEET.

THIS TECHNICAL DATA SHEET IS IDENTIFIED AS **ZUOSI 1 (0922) E**